

Table S1. Se3d XPS map fitting curve information

Name	Binding Energy (ev)	Atomic (%)
Se3d _{5/2}	54.63	38.01
Se3d _{3/2}	55.51	58.05
Se3d	56.95	3.94